

TUBO AÇO ZINCADO





Tubo em aço Zincado.





Zincagem electrolítica exterior e tratamento com Cromo III, espessuras padrão de 8 a 15 microns, sem cromo IV, de acordo com as Diretivas Europeias EN 2000/53/CE e EN 10305-4 - E235 + N St37.4

Vendido em lances de 3m

ou 6m (sob consulta)



			
mm	PRESSÃO BAR	RUTURA BAR	KG/M
4 x 1.0	624	2495	0.701
6 x 2.0	989	3955	0.211
6 x 1.5	624	2495	0.171
6 x 1.0	365	1460	0.121
8x2	624	2495	0.296
8 x 1.5	423	1692	0.241
8 x 1.0	259	1036	0.171
10 x 2.5	624	2495	0.461
10 x 1.5	321	1284	0.311
10 x 1.0	201	803	0.221
12 x 3.0	624	2495	0.741
12 X 2.0	365	1460	0.501
12 x 1.5	259	1036	0.391
12 x 1.0	164	656	0.271
14 x 3.0	504	2015	0.821
14 x 2.0	303	1211	0.591
15 x 2.0	279	1117	0.641
15 x 1.5	201	803	0.501
16 x 3.0	423	1692	0.961
16 x 2.0	259	1036	0.691
			0
18 x 2.0	226	905	0.791
18 x 1.5	164	656	0.611
20 x 3.0	321	1284	1.261
20 x 2.5	259	1036	1.011
20 x 2.0	201	803	0.891
22 x 2.0	181	722	0.991
22 x 1.5	132	528	0.701
25 x 4.0	347	1388	2.071
25 x 3.0	247	988	1.631
25 x 2.5	201	803	1.391
28 x 3.0	217	868	1.851
28 x 2.0	139	555	1.281
30 x 4.0	279	1117	2.571
30 x 3.0	201	803	2

			
mm	PRESSÃO BAR	RUTURA BAR	KG/M
30 x 3.0	201	803	2
35 x 3.0	169	677	2.371
35 x 2.0	109	437	1.631
38 x 5.0	275	1099	4.071
38 x 4.0	213	851	3.351
42 x 3.0	139	555	2.891